



**AMENDMENTS TO THE CLAIMS:**

This listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Original) A rotogravure coated paper comprising a coating layer containing a pigment and an adhesive on a base paper, wherein the coating layer contains an inorganic pigment having a volume-based distribution in which 65% or more of particles are in the particle diameter range of 0.4-4.2  $\mu\text{m}$  and a hollow sphere synthetic pigment having a mean particle diameter of 0.1-0.6  $\mu\text{m}$ .
2. (Currently Amended) The rotogravure coated paper of claim 1 characterized in that wherein the hollow sphere synthetic pigment is contained present in an amount of 2-30 parts by weight per 100 parts by weight of the inorganic pigment.
3. (Currently Amended) The rotogravure coated paper of claim 1 characterized in that wherein 3-12% by weight of an amorphous silicate is contained on the basis of based on the weight of the base paper is present.
4. (Currently Amended) The rotogravure coated paper of claim 1 characterized in that wherein 75 parts by weight or more of kaolin is included as an inorganic pigment component in per 100 parts by weight of the inorganic pigment.
5. (Previously Presented) A process for preparing the rotogravure coated paper of claim 1.